



DuPont Teijin Films™

MELINEX® 516

Product Description

Melinex® 516 is a high clarity polyester film which is pretreated on both sides for slip to combine good handling properties with high clarity and brilliance.

Typical Applications

Some typical uses include: layout base, post lamination, MTS, color proofing, labels, flexible circuits, archival sheeting, and printing plates.

Approvals

UL 94 VTM-2 - for 300 - 700 gauge (0.076 - 0.18mm)

Library of Congress Specification - This film meets the Library of Congress Specification Number 500-500-5/31/95 for use in archival storage.

Typical Properties

Available Thickness [Gauge]

250; 265; 275; 300; 360; 370; 400; 460; 500; 600

Property	Thickness	Value	Units	Test
OPTICAL				
Total Light Transmission (TLT)	265	88.5	%	ASTM D1003
Total Light Transmission (TLT)	300	88.5	%	ASTM D1003
Total Light Transmission (TLT)	400	88.3	%	ASTM D1003
Total Light Transmission (TLT)	500	88.0	%	ASTM D1003
PHYSICAL				
C.O.F. (dynamic) A-B		0.45		ASTM D1894
Elongation at Break MD		180	%	ASTM D882A
Elongation at Break TD		120	%	ASTM D882A
Tensile Strength MD		28,000	psi	ASTM D882A
Tensile Strength TD		35,000	psi	ASTM D882A
Yield Strength MD		14,000	psi	ASTM D882A
Yield Strength TD		14,500	psi	ASTM D882A
THERMAL				
Shrinkage MD (190°C)		2.5	%	Unrestrained @ 190°C/5 min
Shrinkage TD (190°C)		1.0	%	Unrestrained @ 190°C/5 min

Contact Info

DuPont Teijin Films U.S. Limited Partnership
 3600 Discovery Drive
 Chester, VA 23836 USA
 Tel: (800) 635-4639
 Fax: (804) 530-9867

Disclaimer

Note: These values are typical performance data for DuPont Teijin Films' polyester film; they are not intended to be used as design data. We believe this information is the best currently available on the subject. It is offered as a possible helpful suggestion in experimentation you may care to undertake along these lines. It is subject to revision as

additional knowledge and experience is gained. DuPont Teijin Films makes no guarantee of results and assumes no obligation or liability whatsoever in connection with this information. This publication is not a license to operate under, or intended to suggest infringement of, any existing patents.

CAUTION: Do not use in medical applications involving permanent implantation in the human body ([DuPont Teijin Films Medical Policy](#)). For other medical applications, see the [Medical Caution Statement](#). DuPont Teijin Films accepts no liability for use of its products in medical applications not reviewed and approved by DuPont Teijin Films or for product misuse. DuPont Teijin Films supplies products to an agreed specification and does not manufacture products designed specifically for medical end use.

Melinex®, Mylar® and Melinex® ST™ are registered trademarks of DuPont Teijin Films U.S. Limited Partnership. Teijin® and Tetoron® are registered trademarks of Teijin Limited used under license by DuPont Teijin Films U.S. Limited Partnership. Teonex® is a registered trademark of Teijin DuPont Films Japan Limited and is used under license by DuPont Teijin Films U.S. Limited Partnership.